

# DIN EN 680:2006-03 (E)

## Determination of the drying shrinkage of autoclaved aerated concrete

---

### Contents

	Page
<b>Foreword .....</b>	<b>3</b>
<b>1 Scope .....</b>	<b>4</b>
<b>2 Normative references .....</b>	<b>4</b>
<b>3 Principle .....</b>	<b>4</b>
<b>4 Apparatus .....</b>	<b>4</b>
<b>5 Test specimens .....</b>	<b>5</b>
<b>5.1 Sample .....</b>	<b>5</b>
<b>5.2 Shape and size of the test specimens .....</b>	<b>5</b>
<b>5.3 Number of test specimens .....</b>	<b>5</b>
<b>5.4 Preparation of test specimens .....</b>	<b>6</b>
<b>5.5 Measurement of dimensions of test specimens and determination of their volume .....</b>	<b>6</b>
<b>5.6 Conditioning of test specimens .....</b>	<b>7</b>
<b>6 Testing procedure .....</b>	<b>7</b>
<b>6.1 Drying storage in a climate at <math>(20 \pm 2)^\circ\text{C}</math> and <math>(45 \pm 5)\%</math> relative humidity and determination of length changes and variations of mass .....</b>	<b>7</b>
<b>6.2 Drying of test specimens at <math>(105 \pm 5)^\circ\text{C}</math> .....</b>	<b>7</b>
<b>7 Test results .....</b>	<b>8</b>
<b>7.1 Calculation of relative length change .....</b>	<b>8</b>
<b>7.2 Calculation of moisture content .....</b>	<b>8</b>
<b>7.3 Determination of the conventional reference value of drying shrinkage .....</b>	<b>8</b>
<b>7.4 Determination of the total value of drying shrinkage .....</b>	<b>9</b>
<b>7.5 Calculation of the dry density .....</b>	<b>9</b>
<b>8 Test report .....</b>	<b>9</b>