

DIN EN 680:2006-03 (E)

Determination of the drying shrinkage of autoclaved aerated concrete

| Contents | | Page |
|-----------------|--|-------------|
| Foreword | | 3 |
| 1 | Scope | 4 |
| 2 | Normative references | 4 |
| 3 | Principle | 4 |
| 4 | Apparatus | 4 |
| 5 | Test specimens | 5 |
| 5.1 | Sample | 5 |
| 5.2 | Shape and size of the test specimens | 5 |
| 5.3 | Number of test specimens | 5 |
| 5.4 | Preparation of test specimens | 6 |
| 5.5 | Measurement of dimensions of test specimens and determination of their volume | 6 |
| 5.6 | Conditioning of test specimens | 7 |
| 6 | Testing procedure | 7 |
| 6.1 | Drying storage in a climate at (20 ± 2) °C and (45 ± 5) % relative humidity and determination of length changes and variations of mass | 7 |
| 6.2 | Drying of test specimens at (105 ± 5) °C | 7 |
| 7 | Test results | 8 |
| 7.1 | Calculation of relative length change | 8 |
| 7.2 | Calculation of moisture content | 8 |
| 7.3 | Determination of the conventional reference value of drying shrinkage | 8 |
| 7.4 | Determination of the total value of drying shrinkage | 9 |
| 7.5 | Calculation of the dry density | 9 |
| 8 | Test report | 9 |