

DIN EN 680:2006-03 (E)

Determination of the drying shrinkage of autoclaved aerated concrete

Contents		Page
Foreword		3
1	Scope	4
2	Normative references	4
3	Principle	4
4	Apparatus	4
5	Test specimens	5
5.1	Sample	5
5.2	Shape and size of the test specimens	5
5.3	Number of test specimens	5
5.4	Preparation of test specimens	6
5.5	Measurement of dimensions of test specimens and determination of their volume	6
5.6	Conditioning of test specimens	7
6	Testing procedure	7
6.1	Drying storage in a climate at (20 ± 2) °C and (45 ± 5) % relative humidity and determination of length changes and variations of mass	7
6.2	Drying of test specimens at (105 ± 5) °C	7
7	Test results	8
7.1	Calculation of relative length change	8
7.2	Calculation of moisture content	8
7.3	Determination of the conventional reference value of drying shrinkage	8
7.4	Determination of the total value of drying shrinkage	9
7.5	Calculation of the dry density	9
8	Test report	9