

DIN EN 12732:2013-07 (E)

Gas infrastructure - Welding steel pipework - Functional requirements

Contents		Page
Foreword		5
1	Scope	6
2	Normative references	8
3	Terms and definitions	10
4	Quality system	13
4.1	General	13
4.2	Welding contractors	14
4.3	Welders	14
4.4	Welding supervisory and coordination personnel	14
4.5	Testing companies and personnel	14
4.5.1	General	14
4.5.2	Non-destructive testing (NDT)	14
4.5.3	Destructive testing (DT)	15
5	Welding consumables	15
6	Production welding	17
6.1	General requirements	17
6.1.1	General	17
6.1.2	Working area	17
6.1.3	Layout of weld joints	17
6.1.4	Types of weld joints	17
6.1.5	Joint edge preparation	17
6.1.6	Weld fit-up	17
6.1.7	Different wall thickness	17
6.1.8	Pipe branches and nozzles	17
6.1.9	Laminations	17
6.1.10	Butt welds cross joints	17
6.2	Joint preparation	18
6.2.1	Pipe end preparation	18
6.2.2	Alignment of the joints	18
6.3	Preheating	18
6.4	Tacking	18
6.5	Welding	18
6.6	Actions after welding	19
6.7	Repair of weld defects	19
7	Special procedures	19
7.1	General	19
7.2	Attachment of structural parts	19
7.3	Attachment of cathodic protection connections	20
7.4	Hot-tapping and other welding work on in-service pipelines	20
8	Inspection of the weld joint	20
8.1	General	20
8.2	Scope of inspection	20
8.3	Non-destructive testing and assessment levels	23
8.4	Time of inspection	24

8.5	Acceptance criteria	24
8.6	Recording of test results	25
9	Documentation	25
9.1	General	25
9.2	Archiving requirements	25
10	Specific requirements for gas infrastructure with a MOP up to and including 16 bar	25
10.1	General	25
10.2	Welders	25
10.3	Welding supervisory personnel	26
10.4	Production welding	26
10.4.1	General	26
10.4.2	Joint preparation	26
10.4.3	Welding	26
10.5	Requirements for records and documentation	26
11	Specific requirements for gas infrastructure with a MOP greater than 16 bar	27
11.1	General	27
11.2	Welders	27
11.3	Welding supervisory personnel	27
11.4	Qualification of welding procedures	27
11.4.1	General	27
11.4.2	Filler material requirements for welding procedure qualification	27
11.4.3	Impact testing	28
11.4.4	Transverse tensile test	28
11.4.5	All-weld-metal tensile test	29
11.5	Production welding	29
11.5.1	General	29
11.5.2	Joint preparation	29
11.5.3	Welding	29
11.5.4	Repairs of weld defects	30
11.5.5	Welding consumables	30
11.6	Destructive testing of production welds	30
11.7	Acceptance requirements	30
11.8	Requirements for records and documentation	31
12	Specific requirements for metering, regulating and compressor stations	32
12.1	General	32
12.2	Specific requirements	32
Annex A (informative) Qualification procedure for pipeline welders (Girth welds and branch connections)		33
A.1	General	33
A.2	Approval test	33
A.2.1	Execution of the approval test	33
A.2.2	Range of test pieces	33
A.2.3	Supervision of execution of approval test	34
A.3	Inspection	34
A.3.1	General	34
A.3.2	Testing girth welds	35
A.3.3	Testing weldolets	35
A.4	Approval range	35
A.4.1	General	35
A.4.2	Dimension ranges	35
A.4.3	Techniques	35
A.5	Certificate	36
A.5.1	General	36
A.5.2	Duration of validity	36
Annex B (informative) Testing of lamination defects		37

Annex C (informative) Time-of-flight diffraction technique (TOFD)	38
C.1 General	38
C.2 Additional and substitutional requirements to EN ISO 10863:2011	38
C.2.1 Addition to the whole document EN ISO 10863:2011	38
C.2.2 Addition to EN ISO 10863:2011, Clause 3 "Terms and definitions"	38
C.2.3 Addition to EN ISO 10863:2011, Clause 5, "Examination Levels"	40
C.2.4 Addition to EN ISO 10863:2011, 7.2.2, "Ultrasonic probes"	40
C.2.5 Substitution of EN ISO 10863:2011, Clause 11, 3 rd paragraph "Weld testing"	40
C.2.6 Substitution of EN ISO 10863:2011, 12.5.2 "Sizing"	41
Annex D (informative) Critical aspects for hot-tap welding or welding on in-service pipelines	46
D.1 General	46
D.2 Recommendations	46
D.2.1 Equipment	46
D.2.2 Supervision	46
D.2.3 Safety precautions	46
D.2.4 Identification	46
D.2.5 Filler materials	46
D.3 Weld preparation	47
D.4 Welding procedure specification (WPS)	47
D.4.1 Description of the WPS	47
D.4.2 Qualification of the WPS	47
D.4.3 Approval of the WPS	47
D.5 Qualification of the welder	47
D.6 Precautions	47
D.7 Execution	48
D.8 Repairs	48
D.9 WPS qualification record	48
Annex E (informative) Visual examination of joints	50
E.1 General	50
E.2 Recommendations	50
Annex F (informative) Manual ultrasonic testing of weld joints for wall thickness between approximately 6 mm and 8 mm	51
F.1 General	51
F.2 Setting	51
F.2.1 Setting of range	51
F.2.2 Sensitivity adjustment when using the Distance Gain Size method	51
Annex G (normative) Acceptance criteria - Recommendations for on-site production welds	55
G.1 General	55
G.2 Acceptance criteria according to EN ISO 5817	55
G.3 Summary of requirements for defect acceptance levels and defect limits	58
G.3.1 General	58
G.3.2 Requirements	59
G.4 Method and acceptance criteria for ultrasonic inspection assessment	66
G.4.1 Distance Gain Size method	66
G.4.2 Comparative Element method	66
G.4.3 General	67
G.4.4 Assessment of indications using automatic pulse-echo technique	68
Annex H (informative) Brazing and aluminothermic welding of leads for cathodic protection systems	69
H.1 Joining techniques	69

H.2	Procedure qualification	69
H.3	Operation qualification	71
H.4	Production joints	71
Annex I (informative) Significant technical changes between this European Standard and the previous edition		72
Bibliography		74