

ISO 4802-2:2023-12 (E)

Glassware - Hydrolytic resistance of the interior surfaces of glass containers - Part 2: Determination by flame spectrometry and classification

Contents		Page
	Foreword	iv
	Introduction	v
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	4
5	Reagents	4
6	Apparatus	6
7	Sample preparation	7
7.1	Sample size.....	7
7.2	Determination of the filling volume.....	7
7.2.1	Flat-bottomed containers ≤ 20 mm outer flange diameter (except ampoules, syringes and cartridges).....	7
7.2.2	Flat-bottomed containers > 20 mm outer flange diameter.....	7
7.2.3	Round-bottomed containers.....	8
7.2.4	Lipped containers.....	8
7.2.5	Ampoules.....	8
7.2.6	Syringes and cartridges.....	8
8	Procedure	9
8.1	General.....	9
8.2	Cleaning of samples.....	9
8.3	Filling and heating.....	9
8.4	Analysis of the extraction solutions.....	10
8.4.1	Containers of hydrolytic resistance container classes HC _F 1, HC _F 2 and HC _F B or those known to be made from borosilicate glass.....	10
8.4.2	Containers of hydrolytic resistance container classes HC _F 3 and HC _F D, or those known to be made from soda-lime-silica glass.....	10
8.5	Test to determine whether the containers have been surface-treated.....	11
9	Expression of results	12
9.1	Determination.....	12
9.2	Classification.....	12
9.3	Distinction between containers of hydrolytic resistance container class HC _F 1 and hydrolytic resistance container class HC _F 2.....	13
9.4	Designation.....	13
10	Test report	13
11	Reproducibility	13
	Bibliography	15