

DIN ISO 4802-2:2024-08 (E)

Glassware - Hydrolytic resistance of the interior surfaces of glass containers - Part 2: Determination by flame spectrometry and classification (ISO 4802-2:2023)

Contents		Page
National foreword		3
National Annex NA (informative) Bibliography		5
Foreword		6
Introduction		7
1	Scope	8
2	Normative references	8
3	Terms and definitions	8
4	Principle	11
5	Reagents	11
6	Apparatus	13
7	Sample preparation	14
7.1	Sample size	14
7.2	Determination of the filling volume	14
7.2.1	Flat-bottomed containers ≤ 20 mm outer flange diameter (except ampoules, syringes and cartridges)	14
7.2.2	Flat-bottomed containers > 20 mm outer flange diameter	14
7.2.3	Round-bottomed containers	15
7.2.4	Lipped containers	15
7.2.5	Ampoules	15
7.2.6	Syringes and cartridges	15
8	Procedure	16
8.1	General	16
8.2	Cleaning of samples	16
8.3	Filling and heating	16
8.4	Analysis of the extraction solutions	17
8.4.1	Containers of hydrolytic resistance container classes HC _F 1, HC _F 2 and HC _F B or those known to be made from borosilicate glass	17
8.4.2	Containers of hydrolytic resistance container classes HC _F 3 and HC _F D, or those known to be made from soda-lime-silica glass	17
8.5	Test to determine whether the containers have been surface-treated	18
9	Expression of results	19
9.1	Determination	19
9.2	Classification	19
9.3	Distinction between containers of hydrolytic resistance container class HC _F 1 and hydrolytic resistance container class HC _F 2	20
9.4	Designation	20
10	Test report	20
11	Reproducibility	20
Bibliography		22