

# DIN EN 1254-20:2025-04 (E)

Copper and copper alloys - Plumbing fittings - Part 20: Definitions, thread dimensions, test methods, reference data and supporting information (includes Amendment A1:2025)

---

<b>Contents</b>		<b>Page</b>
European foreword .....		5
<b>1</b>	<b>Scope .....</b>	<b>6</b>
<b>2</b>	<b>Normative references .....</b>	<b>6</b>
<b>3</b>	<b>Terms and definitions .....</b>	<b>7</b>
<b>4</b>	<b>Thread dimensions .....</b>	<b>10</b>
<b>4.1</b>	<b>Wall thickness at threaded portions of fittings .....</b>	<b>10</b>
<b>4.2</b>	<b>Dimensions of tail pipe ends for swivel fittings .....</b>	<b>11</b>
<b>4.3</b>	<b>Dimensions of gas union connectors .....</b>	<b>13</b>
<b>4.4</b>	<b>Threaded end dimensions .....</b>	<b>14</b>
<b>4.5</b>	<b>Minimum bore and cross-sectional area of fittings .....</b>	<b>20</b>
<b>5</b>	<b>Test method for leak tightness under internal hydrostatic pressure .....</b>	<b>24</b>
<b>5.1</b>	<b>Introduction .....</b>	<b>24</b>
<b>5.2</b>	<b>Principle .....</b>	<b>25</b>
<b>5.3</b>	<b>Apparatus .....</b>	<b>25</b>
<b>5.4</b>	<b>Test piece .....</b>	<b>25</b>
<b>5.5</b>	<b>Procedure .....</b>	<b>26</b>
<b>6</b>	<b>Test method for leak tightness under internal pneumatic pressure .....</b>	<b>26</b>
<b>6.1</b>	<b>Introduction .....</b>	<b>26</b>
<b>6.2</b>	<b>Principle .....</b>	<b>26</b>
<b>6.3</b>	<b>Apparatus .....</b>	<b>27</b>
<b>6.4</b>	<b>Test piece .....</b>	<b>27</b>
<b>6.5</b>	<b>Procedure .....</b>	<b>28</b>
<b>7</b>	<b>Integrity of fabricated fitting bodies or having an 'as cast' microstructure .....</b>	<b>29</b>
<b>7.1</b>	<b>Introduction .....</b>	<b>29</b>
<b>7.2</b>	<b>Principle .....</b>	<b>29</b>
<b>7.3</b>	<b>Apparatus .....</b>	<b>29</b>
<b>7.4</b>	<b>Test piece .....</b>	<b>29</b>
<b>7.5</b>	<b>Procedure .....</b>	<b>30</b>
<b>8</b>	<b>Test method for resistance to pull out of joints to metallic tubes .....</b>	<b>30</b>
<b>8.1</b>	<b>Introduction .....</b>	<b>30</b>
<b>8.2</b>	<b>Principle .....</b>	<b>30</b>
<b>8.3</b>	<b>Apparatus .....</b>	<b>30</b>
<b>8.4</b>	<b>Test assembly .....</b>	<b>31</b>
<b>8.5</b>	<b>Procedure .....</b>	<b>31</b>
<b>9</b>	<b>Test method for the resistance of joints with metallic tube to vibration .....</b>	<b>31</b>
<b>9.1</b>	<b>Introduction .....</b>	<b>31</b>
<b>9.2</b>	<b>Principle .....</b>	<b>31</b>
<b>9.3</b>	<b>Apparatus .....</b>	<b>32</b>
<b>9.4</b>	<b>Test assembly .....</b>	<b>32</b>
<b>9.5</b>	<b>Procedure .....</b>	<b>33</b>

<b>10</b>	<b>Test method for the resistance of joints to static flexural force .....</b>	<b>33</b>
<b>10.1</b>	<b>Introduction .....</b>	<b>33</b>
<b>10.2</b>	<b>Principle .....</b>	<b>33</b>
<b>10.3</b>	<b>Apparatus .....</b>	<b>33</b>
<b>10.4</b>	<b>Test piece .....</b>	<b>33</b>
<b>10.5</b>	<b>Procedure .....</b>	<b>34</b>
<b>11</b>	<b>Test method for leak tightness of joints under vacuum .....</b>	<b>35</b>
<b>11.1</b>	<b>Introduction .....</b>	<b>35</b>
<b>11.2</b>	<b>Principle .....</b>	<b>35</b>
<b>11.3</b>	<b>Apparatus .....</b>	<b>35</b>
<b>11.4</b>	<b>Test piece .....</b>	<b>36</b>
<b>11.5</b>	<b>Procedure .....</b>	<b>36</b>
<b>12</b>	<b>Test method for the resistance of joints to temperature cycling (liquid applications) .....</b>	<b>37</b>
<b>12.1</b>	<b>Introduction .....</b>	<b>37</b>
<b>12.2</b>	<b>Principle .....</b>	<b>37</b>
<b>12.3</b>	<b>Apparatus .....</b>	<b>37</b>
<b>12.4</b>	<b>Test assembly .....</b>	<b>37</b>
<b>12.5</b>	<b>Procedure .....</b>	<b>39</b>
<b>13</b>	<b>Test method for the resistance of joints to temperature cycling (fuel gas applications) ....</b>	<b>39</b>
<b>13.1</b>	<b>Introduction .....</b>	<b>39</b>
<b>13.2</b>	<b>Principle .....</b>	<b>40</b>
<b>13.3</b>	<b>Apparatus .....</b>	<b>40</b>
<b>13.4</b>	<b>Test assembly .....</b>	<b>40</b>
<b>13.5</b>	<b>Procedure .....</b>	<b>40</b>
<b>14</b>	<b>Method for detecting non-pressed fitting ends .....</b>	<b>41</b>
<b>14.1</b>	<b>Introduction .....</b>	<b>41</b>
<b>14.2</b>	<b>Principle .....</b>	<b>41</b>
<b>14.3</b>	<b>Apparatus .....</b>	<b>41</b>
<b>14.4</b>	<b>Test piece .....</b>	<b>42</b>
<b>14.5</b>	<b>Procedure .....</b>	<b>42</b>
<b>14.6</b>	<b>Results .....</b>	<b>42</b>
<b>15</b>	<b>Determination of resistance to stress corrosion .....</b>	<b>43</b>
<b>15.1</b>	<b>Introduction .....</b>	<b>43</b>
<b>15.2</b>	<b>Test piece .....</b>	<b>43</b>
<b>15.3</b>	<b>Procedure .....</b>	<b>43</b>
<b>15.4</b>	<b>Test report .....</b>	<b>43</b>
<b>16</b>	<b>Test method for detection of a carbon film on the surface of copper fittings .....</b>	<b>43</b>
<b>16.1</b>	<b>Preparation of the test piece .....</b>	<b>43</b>
<b>16.2</b>	<b>Procedure .....</b>	<b>43</b>
<b>16.3</b>	<b>Detection and assessment of films .....</b>	<b>44</b>
<b>17</b>	<b>Determination of mean depth of dezincification .....</b>	<b>44</b>
<b>17.1</b>	<b>Introduction .....</b>	<b>44</b>
<b>17.2</b>	<b>Procedure .....</b>	<b>44</b>
<b>17.3</b>	<b>Expression of results .....</b>	<b>44</b>
<b>18</b>	<b>Test method for the resistance of joints to pressure cycling .....</b>	<b>45</b>
<b>18.1</b>	<b>Introduction .....</b>	<b>45</b>
<b>18.2</b>	<b>Principle .....</b>	<b>45</b>
<b>18.3</b>	<b>Apparatus .....</b>	<b>45</b>
<b>18.4</b>	<b>Test pieces .....</b>	<b>47</b>
<b>18.5</b>	<b>Procedure .....</b>	<b>47</b>
<b>19</b>	<b>Test method for disconnection and re-use .....</b>	<b>48</b>
<b>19.1</b>	<b>Introduction .....</b>	<b>48</b>

19.2	Principle .....	48
19.3	Apparatus .....	48
19.4	Test assembly .....	48
19.5	Procedure .....	48
20	Method for determining if the diameter and/or the length of engagement of a capillary end is/are within the specified tolerance .....	48
20.1	Principle .....	48
20.2	Apparatus .....	49
20.3	Test piece .....	53
20.4	Procedure .....	53
20.5	Results .....	53
21	Method for determining the minimum length of engagement of an integral solder or brazing ring socket having a formed groove .....	53
21.1	Introduction .....	53
21.2	Principle .....	53
21.3	Apparatus .....	53
21.4	Test piece .....	54
21.5	Procedure .....	54
21.6	Results .....	54
22	"Minimum wall thickness" .....	55
Annex A (informative) Assembling instructions .....		56
Bibliography .....		64