

# ISO 5771:2024-04 (E)

## Rubber hoses and hose assemblies for transferring anhydrous ammonia - Specification

---

<b>Contents</b>		<b>Page</b>
Foreword .....		iv
<b>1</b>	<b>Scope .....</b>	<b>1</b>
<b>2</b>	<b>Normative references .....</b>	<b>1</b>
<b>3</b>	<b>Terms and definitions .....</b>	<b>1</b>
<b>4</b>	<b>Pressure rating .....</b>	<b>2</b>
<b>5</b>	<b>Materials and construction .....</b>	<b>2</b>
<b>5.1</b>	<b>Lining .....</b>	<b>2</b>
<b>5.2</b>	<b>Reinforcement .....</b>	<b>2</b>
<b>5.3</b>	<b>Cover .....</b>	<b>2</b>
<b>5.4</b>	<b>Hose assemblies .....</b>	<b>2</b>
<b>6</b>	<b>Dimensions .....</b>	<b>3</b>
<b>6.1</b>	<b>Inside diameters and tolerances .....</b>	<b>3</b>
<b>6.2</b>	<b>Outside diameter .....</b>	<b>3</b>
<b>6.3</b>	<b>Concentricity .....</b>	<b>3</b>
<b>6.4</b>	<b>Tolerances on length .....</b>	<b>3</b>
<b>7</b>	<b>Physical properties .....</b>	<b>3</b>
<b>7.1</b>	<b>Rubber compounds .....</b>	<b>3</b>
<b>7.2</b>	<b>Finished hose .....</b>	<b>4</b>
<b>7.3</b>	<b>Ammonia resistance tests .....</b>	<b>4</b>
<b>7.3.1</b>	<b>Test lengths .....</b>	<b>5</b>
<b>7.3.2</b>	<b>Ammonia conditioning .....</b>	<b>5</b>
<b>7.3.3</b>	<b>Flexing of conditioned hose .....</b>	<b>7</b>
<b>7.3.4</b>	<b>Burst-pressure test on conditioned and flexed hoses .....</b>	<b>8</b>
<b>7.3.5</b>	<b>Physical-property tests on conditioned and flexed hoses .....</b>	<b>8</b>
<b>8</b>	<b>Hose assembly delivery test and annual in-use test requirements .....</b>	<b>8</b>
<b>9</b>	<b>Frequency of testing .....</b>	<b>8</b>
<b>10</b>	<b>Marking .....</b>	<b>9</b>
<b>11</b>	<b>Packaging and storage .....</b>	<b>9</b>
<b>12</b>	<b>Test certificate .....</b>	<b>9</b>
<b>Annex A (normative) Type frequency for type tests and routine tests .....</b>		<b>10</b>
<b>Annex B (informative) Recommendations for the lengths of hoses supplied in bulk and for tolerances on the lengths of hose assemblies .....</b>		<b>12</b>
<b>Bibliography .....</b>		<b>13</b>