

ISO 22762-2:2024-09 (E)

Elastomeric seismic-protection isolators - Part 2: Applications for bridges - Specifications

Contents		Page
Foreword		v
Introduction		vi
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Symbols	3
5	Classification	6
5.1	General	6
5.2	Classification by construction	6
5.3	Classification by tolerances on shear stiffness	7
6	Requirements	7
6.1	General	7
6.2	Type tests and routine tests	7
6.3	Functional requirements	9
6.4	Design compressive force and design shear displacement	10
6.5	Performance requirements	10
6.5.1	General	10
6.5.2	Compressive properties	10
6.5.3	Rotation properties	11
6.5.4	Shear properties	11
6.5.5	Tensile properties	12
6.5.6	Dependencies of shear properties	12
6.5.7	Shear displacement capacity	13
6.5.8	Durability	14
6.5.9	Cyclic compressive fatigue properties	14
6.5.10	Reaction force characteristics at low-rate deformation	15
6.6	Rubber material requirements	15
6.6.1	General	15
6.6.2	Tensile properties	15
6.6.3	Properties after ageing in air	15
6.6.4	Hardness	16
6.6.5	Adhesion properties	16
6.6.6	Compression set	16
6.6.7	Ozone resistance	17
6.6.8	Other properties	17
6.7	Dimensional requirements	17
6.8	Requirements on steel used for flanges and reinforcing plates	17
7	Design rules	17
7.1	General	17
7.2	Shape factor	19
7.2.1	First shape factor	19
7.2.2	Second shape factor	19
7.3	Compressive and shear properties	20

7.3.1	Compressive stiffness	20
7.3.2	Shear stiffness and equivalent damping ratio	20
7.4	Shear strain due to horizontal displacements	20
7.5	Total local shear strain	21
7.5.1	Local shear strain due to compressive force	21
7.5.2	Local shear strain due to compressive force	21
7.5.3	Total local shear strain	21
7.6	Tensile stress on reinforcing steel plates	22
7.7	Stability	22
7.7.1	Maximum compressive stress in non-seismic condition	22
7.7.2	Rotation performance check	22
7.7.3	Buckling check	23
7.7.4	Tensile stress on elastomeric isolator	23
7.8	Force, moment and deformation affecting structures	23
7.8.1	Shear force affecting structures due to movement	23
7.8.2	Resistance to rotation	23
7.8.3	Compressive displacement due to compressive force	24
7.9	Design of fixings	24
7.9.1	External forces affecting joint members	24
7.9.2	Fixings and stresses to be checked	24
7.9.3	Allowable stress	25
8	Manufacturing tolerances	25
8.1	General	25
8.2	Measuring instruments	25
8.3	Plan dimensions of elastomeric isolator body	26
8.3.1	Measurement method (see Figure 1)	26
8.3.2	Tolerances	26
8.4	Product height	27
8.4.1	Measurement method	27
8.4.2	Tolerances	28
8.5	Flatness of products	28
8.5.1	Measurement method	28
8.5.2	Tolerances	29
8.6	Horizontal offset	29
8.6.1	Measurement method	29
8.6.2	Tolerances	29
8.7	Plan dimensions of flanges	29
8.8	Flange thickness	30
8.9	Tolerances on positions of flange bolt holes	30
9	Marking and labelling	30
9.1	Information to be provided	31
9.2	Additional requirements	31
9.3	Marking and labelling examples	31
10	Test methods	31
11	Quality assurance	32
	Annex A (normative) Tensile stress in reinforcing steel plate	33
	Annex B (normative) Buckling stability	35
	Annex C (normative) Allowable tensile stress in elastomeric isolator	36
	Annex D (informative) Dependence of ultimate properties on shape factor	37
	Annex E (informative) Minimum recommended tensile properties for rubber materials	41
	Annex F (informative) Compressive stiffness	42

Annex G (informative) Determination of shear properties of elastomeric isolators46
Annex H (informative) Determination of local shear strain due to compression 51
Annex I (informative) Maximum compressive stress 54
Bibliography55