

# ISO 5999:2007-11 (E)

## Flexible cellular polymeric materials - Polyurethane foam for load-bearing applications excluding carpet underlay - Specification

---

<b>Contents</b>		<b>Page</b>
Foreword .....		iv
<b>1</b>	<b>Scope .....</b>	<b>1</b>
<b>2</b>	<b>Normative references .....</b>	<b>1</b>
<b>3</b>	<b>Classification .....</b>	<b>2</b>
<b>3.1</b>	<b>Type .....</b>	<b>2</b>
<b>3.2</b>	<b>Class .....</b>	<b>2</b>
<b>3.3</b>	<b>Grade .....</b>	<b>6</b>
<b>4</b>	<b>Material .....</b>	<b>7</b>
<b>5</b>	<b>Construction .....</b>	<b>7</b>
<b>6</b>	<b>Surface condition .....</b>	<b>7</b>
<b>7</b>	<b>Odour .....</b>	<b>7</b>
<b>8</b>	<b>Colour .....</b>	<b>7</b>
<b>9</b>	<b>Component mass and density .....</b>	<b>7</b>
<b>10</b>	<b>Dimensions .....</b>	<b>8</b>
<b>11</b>	<b>Physical and chemical requirements .....</b>	<b>8</b>
<b>12</b>	<b>Burning characteristics .....</b>	<b>10</b>
<b>13</b>	<b>Test methods .....</b>	<b>10</b>
<b>13.1</b>	<b>Test conditions .....</b>	<b>10</b>
<b>13.2</b>	<b>Density .....</b>	<b>10</b>
<b>13.3</b>	<b>Hardness .....</b>	<b>10</b>
<b>13.4</b>	<b>Resilience .....</b>	<b>10</b>
<b>13.5</b>	<b>Compression set .....</b>	<b>11</b>
<b>13.6</b>	<b>Dynamic fatigue by constant-load pounding .....</b>	<b>11</b>
<b>13.7</b>	<b>Tensile strength and elongation at break .....</b>	<b>11</b>
<b>13.8</b>	<b>Burning behaviour .....</b>	<b>11</b>
<b>13.9</b>	<b>Heat ageing .....</b>	<b>11</b>
<b>13.10</b>	<b>Humidity ageing .....</b>	<b>11</b>
<b>14</b>	<b>Marking .....</b>	<b>11</b>
<b>Annex A (informative) Typical applications for each class of material .....</b>		<b>12</b>
<b>Annex B (informative) Burning properties of flexible polyurethane foam and recommendations regarding its use .....</b>		<b>13</b>
<b>Annex C (informative) Main details of revision .....</b>		<b>15</b>