

# DIN EN 1965-2:2011-07 (E)

## Structural adhesives - Corrosion - Part 2: Determination and classification of corrosion to a brass substrate

---

<b>Contents</b>		<b>Page</b>
Foreword .....		3
1	Scope .....	4
2	Normative references .....	4
3	Terms and definitions .....	4
4	Principle .....	4
5	Products, materials and apparatus .....	4
5.1	Solvent .....	4
5.2	Brass electrode, consisting of 0,1 mm thick brass, Ms63F45 or Ms63F55 of width 10 mm ...	4
5.3	Etching solution, consisting of 73 % concentrated sulfuric acid (98 %), 26 % concentrated nitric acid (63 %), 0,5 % sodium chloride, 0,5 % carbon black .....	4
5.4	Conditioning chamber, capable of maintaining a hot/humid climate in accordance with EN ISO 291 .....	5
5.5	Direct current source, (100 ± 5) V, e.g. a battery, or rectifying equipment with a maximum permissible electrodyne alternating current not greater than 1 % .....	5
5.6	Magnifier, with a magnification of 2,5 × .....	5
5.7	Electrode and clamping, in accordance with Figure 1 .....	5
6	Preparation of the brass substrate .....	7
7	Test specimens .....	7
8	Procedure .....	7
9	Discolouration/corrosion .....	8
10	Test report .....	8
Annex A (normative) Gradings for the appearance of plus pole and minus pole test foils at the surface of contact at the test specimen .....		9
Bibliography .....		10