

DIN EN 933-1:2012-03 (E)

Tests for geometrical properties of aggregates - Part 1: Determination of particle size distribution - Sieving method

Contents		Page
Foreword		3
1	Scope	4
2	Normative references	4
3	Terms and definitions	4
4	Principle	5
5	Apparatus	5
6	Preparation of test portions	5
7	Procedure	6
7.1	Washing	6
7.2	Sieving	7
7.3	Weighing	8
8	Calculation and expression of results	8
8.1	Calculations	8
8.2	Validating the results	8
8.3	Precision	9
9	Test report	9
9.1	Required data	9
9.2	Optional data	9
Annex A (normative) Alternative test method for all-in aggregate with D 31,5 mm		11
A.1	Principle	11
A.2	Apparatus	11
A.3	Procedure	11
A.3.1	Preparation of the initial test portion	11
A.3.2	First washing stage - particles retained on the 16 mm size test sieve	12
A.3.3	First dry sieving stage - particles retained on the 16 mm size test sieve	12
A.3.4	Preparation stage - dry subsample passing the 16 mm size test sieve	12
A.3.5	Second washing stage - reduced subsample passing the 16 mm size test sieve	12
A.3.6	Second dry sieving stage - reduced subsample passing the 16 mm size test sieve	12
A.4	Calculation and expression of results	13
A.4.1	Original dry mass	13
A.4.2	Mass retained on the sieves at the first dry sieving stage	13
A.4.3	Mass retained on the sieves at the second dry sieving stage	13
A.4.4	Mass of fines passing the 0,063 mm sieve	13
A.4.5	Particle size distribution	14
A.4.6	Validating the results	14
Annex B (normative) Test method for aggregates unsuitable for oven-drying		15
Annex C (informative) Example of test data sheet		16

Annex D (informative) Graphical presentation of results	17
Bibliography	18