

ISO 14704:2016-04 (E)

Fine ceramics (advanced ceramics, advanced technical ceramics) - Test method for flexural strength of monolithic ceramics at room temperature

Contents		Page
Foreword		iv
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	3
5	Apparatus	3
5.1	Testing machine	3
5.2	Test fixture	3
5.2.1	General	3
5.2.2	Bearings	4
5.2.3	Four-point fixture: semi-articulating	4
5.2.4	Four-point fixture: fully articulating	4
5.2.5	Three-point fixture: semi-articulating	4
5.2.6	Three-point fixture: fully articulating	5
5.2.7	Positioning of bearings	5
5.2.8	Fixture material	6
5.3	Micrometer	6
6	Test pieces	6
6.1	Test piece size	6
6.1.1	Machined test pieces	6
6.1.2	As-fired or heat-treated test pieces	6
6.2	Test piece preparation	7
6.2.1	General	7
6.2.2	As-fired	7
6.2.3	Customary machining procedure	7
6.2.4	Component-matched procedure	7
6.2.5	Basic machining procedure	7
6.2.6	Parallelism, orthogonality and chamfer sizes	8
6.2.7	Handling of test pieces	9
6.2.8	Number of test pieces	9
7	Procedure	9
8	Calculation	11
9	Test report	12
10	Strength scaling factors	13
Annex A (informative) General information		14
Annex B (normative) Test fixtures		15
Annex C (informative) Typical fracture patterns in ceramic test pieces		21

Annex D (informative) Chamfer correction factors	23
Annex E (informative) Weibull scaling factors	26
Bibliography	28