

DIN EN ISO 19285:2017-12 (E)

Non-destructive testing of welds - Phased array ultrasonic testing (PAUT) - Acceptance levels (ISO 19285:2017)

Contents		Page
European foreword		3
Foreword		4
1	Scope	5
2	Normative references	5
3	Terms and definitions	5
4	Symbols	5
5	Acceptance levels	6
6	Evaluation of indications	6
7	Determination of length and height	6
7.1	General	6
7.2	Determination of length	6
7.3	Determination of height	6
7.3.1	General	6
7.3.2	Using diffracted signals	6
7.3.3	Using other signals	7
8	Determination of length and maximum amplitude	7
9	Acceptance criteria based on length and height	7
9.1	General	7
9.2	Single indications	7
9.2.1	Acceptance criteria for level 1	7
9.2.2	Acceptance criteria for level 2	7
9.2.3	Acceptance criteria for level 3	8
9.3	Cumulative length of indications	8
9.3.1	General	8
9.3.2	For each single set-up	8
9.3.3	Combining set-ups	9
9.4	Grouping of indications	9
9.5	Point-like indications	10
10	Acceptance criteria based on length and amplitude	10
10.1	General	10
10.2	Longitudinal indications	10
10.3	Transverse indications	10
10.4	Grouping of indications	10
10.5	Cumulative length of indications	11
10.5.1	General	11
10.5.2	For each single set-up	12
10.5.3	Combined set-up	12
Annex A (normative) Levels		13
Annex B (normative) Fixed amplitude level technique		26

Annex B (normative) Fixed amplitude level technique	26
--	-----------