

ISO 16962:2017-02 (E)

Surface chemical analysis - Analysis of zinc- and/or aluminium-based metallic coatings by glow-discharge optical emission spectrometry

Contents		Page
Foreword		v
Introduction		vi
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	1
5	Apparatus	2
5.1	Glow-discharge optical emission spectrometer	2
5.1.1	General	2
5.1.2	Selection of spectral lines	2
5.1.3	Selection of glow-discharge source type	2
6	Adjusting the glow-discharge spectrometer system settings	3
6.1	General	3
6.2	Setting the parameters of a DC source	4
6.2.1	Constant applied current and voltage	4
6.2.2	Constant applied current and pressure	5
6.2.3	Constant voltage and pressure	5
6.3	Setting the discharge parameters of an RF source	6
6.3.1	General	6
6.3.2	Constant applied power and pressure	6
6.3.3	Constant applied power and DC bias voltage	6
6.3.4	Constant effective power and effective RF voltage	7
6.4	Minimum performance requirements	7
6.4.1	General	7
6.4.2	Minimum repeatability	7
6.4.3	Detection limit	8
7	Sampling	9
8	Calibration	9
8.1	General	9
8.2	Calibration samples	10
8.2.1	General	10
8.2.2	Brass calibration samples	10
8.2.3	Zn-Al alloy samples	10
8.2.4	Low alloy iron or steel samples	10
8.2.5	Stainless steel samples	10
8.2.6	Nickel alloy samples	10
8.2.7	Aluminium-silicon alloy samples	10
8.2.8	Aluminium-magnesium alloy samples	10
8.2.9	High-purity copper and zinc samples	11
8.3	Validation samples and optional RMs for calibration	11
8.3.1	General	11
8.3.2	Zinc-nickel electrolytically coated RM	11

8.3.3	Zinc-iron electrolytically coated RM	11
8.3.4	Zinc-aluminium hot dip coated RM	11
8.3.5	Zinc-iron hot dip coated and annealed RM	11
8.4	Determination of the sputtering rate of calibration and validation specimens	11
8.5	Emission intensity measurements of calibration specimens	13
8.6	Calculation of calibration equations	13
8.7	Validation using reference materials	13
8.7.1	General	13
8.7.2	Checking analytical accuracy using bulk reference materials	13
8.7.3	Checking analytical accuracy using surface layer reference materials	14
8.8	Verification and drift correction	14
9	Analysis of test specimens	15
9.1	Adjusting discharge parameters	15
9.2	Setting of measuring time and data acquisition rate	15
9.3	Quantifying depth profiles of test specimens	15
10	Expression of results	15
10.1	Expression of quantitative depth profile	15
10.2	Determination of total coating mass per unit area (coating areic mass)	17
10.2.1	General method	17
10.2.2	Method for special applications	17
10.3	Determination of average mass fractions	17
11	Precision	17
12	Test report	18
Annex A (normative)	Calculation of calibration constants and quantitative evaluation of depth profiles	19
Annex B (informative)	Suggestions concerning suitable spectral lines	31
Annex C (informative)	Determination of coating mass per unit area (coating areic mass)	32
Annex D (informative)	Additional information on international cooperative tests	38
Bibliography	40