

ISO 4662:2017-06 (E)

Rubber, vulcanized or thermoplastic - Determination of rebound resilience

Contents		Page
Foreword		v
Introduction		vi
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	2
5	Pendulum method	2
5.1	Apparatus	2
5.1.1	General	2
5.1.2	Oscillatory device	3
5.1.3	System for following the motion of the hammer	3
5.1.4	Test piece holder	3
5.1.5	Temperature control	4
5.1.6	Adjustment of oscillatory device	5
5.2	Test pieces	6
5.2.1	Preparation	6
5.2.2	Dimensions	7
5.2.3	Measurement of dimensions	7
5.2.4	Number of test pieces	7
5.2.5	Time-interval between forming and testing	7
5.2.6	Conditioning	7
5.3	Temperature of test	7
5.4	Procedure	7
5.4.1	Thermal conditioning and mounting of test piece	7
5.4.2	Mechanical conditioning of test piece	8
5.4.3	Measurement of rebound resilience	8
5.4.4	Calculation and expression of results	8
5.5	Precision	8
5.6	Test report	8
6	Tripsometer method	9
6.1	Apparatus	9
6.1.1	General	9
6.1.2	Pendulum	10
6.1.3	System for following the motion of the disc	10
6.1.4	Test piece holder	11
6.1.5	Temperature control	12
6.1.6	Adjustment of oscillatory device	13
6.2	Test pieces	15
6.2.1	Preparation	15
6.2.2	Dimensions	15
6.2.3	Measurement of dimensions	15
6.2.4	Number of test pieces	15
6.2.5	Time-interval between forming and testing	15
6.2.6	Conditioning	15
6.3	Temperature of test	16

6.4	Procedure	16
6.4.1	Thermal conditioning and mounting of test piece	16
6.4.2	Mechanical conditioning of test piece	16
6.4.3	Measurement	16
6.4.4	Calculation and expression of results	16
6.5	Precision	17
6.6	Test report	17
Annex A (informative) Use of non-standard test pieces		18
Annex B (informative) Apparatus designs		21
Annex C (informative) Mounting system for the disc of the tripsometer		22
Annex D (informative) Precision		24
Annex E (informative) Calculation method for the tripsometer's impact velocity		28
Bibliography		31