

ISO 15653:2018-01 (E)

Metallic materials - Method of test for the determination of quasistatic fracture toughness of welds

Contents		Page
Foreword		v
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Symbols and units	3
5	Principle	3
6	Choice of specimen design, specimen orientation and notch location	4
6.1	Classification of target area for notching	4
6.2	Specimen design	4
6.3	Specimen and crack plane orientation	4
7	Pre-machining metallography	8
7.1	Microstructural assessment of macrosections	8
7.2	Additional requirements for heat-affected zone tests	9
8	Machining	9
8.1	Tolerances on specimen dimensions	9
8.2	Notch placement for through-thickness notched specimens	10
8.3	Notch placement for surface-notched specimens	10
8.4	Notch machining	11
9	Specimen preparation	16
9.1	Fatigue precracking	16
9.2	Side grooving	16
10	Test apparatus, requirements and test procedure	16
11	Post-test metallography	16
11.1	General	16
11.2	Through-thickness notched specimens	17
11.2.1	Sectioning	17
11.2.2	Assessment	17
11.3	Surface-notched specimens	17
11.3.1	Sectioning	17
11.3.2	Assessment	17
11.4	Assessment of pop-in	17
12	Post-test analysis	20
12.1	Choice of tensile properties	20
12.2	Determination of fracture toughness	21
12.2.1	K _{Ic}	21
12.2.2	21
12.2.3	J	22
12.2.4	Shallow-notched bend specimen	22
12.3	Qualification requirements	23

12.3.1	General	23
12.3.2	Weld-width-to-crack-ligament ratio	23
12.3.3	Crack front straightness	23
12.3.4	Symbols used to identify fracture toughness values	25
12.3.5	Through-thickness notched specimens	25
12.3.6	Surface-notched specimens	25
13	Test report	26
Annex A (informative) Examples of notch locations		27
Annex B (informative) Examples of pre-test and post-test metallography		29
Annex C (informative) Residual-stress modification and precracking technique		31
Annex D (normative) Assessment of pop-in		35
Annex E (informative) Shallow-notched bend specimen testing		42
Bibliography		45