

ISO 17640:2018 (E)

Non-destructive testing of welds — Ultrasonic testing — Techniques, testing levels, and assessment

Contents

	Foreword
1	Scope
2	Normative references
3	Terms and definitions
4	Symbols
5	General
6	Information required prior to testing
6.1	Items to be specified
6.2	Specific information required before testing
6.3	Written test procedure
7	Requirements for personnel and equipment
7.1	Personnel qualifications
7.2	Test equipment
7.3	Probe parameters
7.3.1	Test frequency
7.3.2	Angles of incidence
7.3.3	Transducer size
7.3.4	Adaptation of probes to curved scanning surfaces
7.3.5	Coupling media
8	Testing volume
9	Preparation of scanning surfaces
10	Parent metal testing
11	Range and sensitivity setting
11.1	General
11.2	Reference for sensitivity setting
11.3	Evaluation levels
11.4	Transfer correction
11.5	Signal-to-noise ratio
12	Testing levels
13	Testing techniques
13.1	General
13.2	Manual scan path
13.3	Testing for imperfections perpendicular to the testing surface
13.4	Location of discontinuities
13.5	Evaluation of indications
13.5.1	General
13.5.2	Maximum echo amplitude
13.5.3	Discontinuity length
13.5.4	Discontinuity height
13.5.5	Characterization of discontinuities

14 Test report

Annex A (normative) Testing levels for various types of welded joints

Page count: 30