

ISO 20601:2018-12 (E)

Non-destructive testing of welds - Ultrasonic testing - Use of automated phased array technology for thin-walled steel components

Contents		Page
Foreword		v
1	Scope	1
2	Normative references	1
3	Terms and definitions	2
4	Testing levels	2
5	Information required before testing	4
5.1	Items to be specified before procedure development	4
5.2	Specific information required by the operator before testing	4
5.3	Written test procedure	4
6	Requirements for personnel and test equipment	5
6.1	Personnel qualifications	5
6.2	Test equipment	5
6.2.1	General	5
6.2.2	Instruments and display	5
6.2.3	Probes	5
6.2.4	Scanning mechanisms	6
7	Preparation for testing	6
7.1	Volume to be tested	6
7.2	Verification of test set-up	6
7.3	Scan increment setting	7
7.4	Geometry considerations	7
7.5	Preparation of scanning surfaces	7
7.6	Temperature	7
7.7	Couplant	7
8	Testing of parent material	7
9	Range and sensitivity settings	8
9.1	Settings	8
9.1.1	General	8
9.1.2	Pulse-echo time window	8
9.1.3	Pulse-echo sensitivity settings	8
9.2	Checking of the settings	8
9.3	Reference blocks	9
9.3.1	General	9
9.3.2	Material	9
9.3.3	Dimensions and shape	9
9.3.4	Reference reflectors	9
9.4	Test blocks testing level D	10
9.4.1	General	10
9.4.2	Material	10
9.4.3	Dimensions and shape	10
9.4.4	Reflectors in test blocks	10

10	Equipment checks	10
11	Verification of the test procedure	11
12	Weld testing	11
13	Data storage	11
14	Interpretation and analysis of phased array data	11
14.1	General	11
14.2	Assessing the quality of the phased array data	12
14.3	Identification of relevant indications	12
14.4	Classification of relevant indications	12
14.5	Determination of location and length	12
14.5.1	Location	12
14.5.2	Length	12
14.6	Indication assessment	13
14.6.1	General	13
14.6.2	Assessment based on amplitude and length	13
14.6.3	Assessment based on height and length	13
14.6.4	Characterization of discontinuities	13
14.7	Evaluation against acceptance criteria	13
15	Test report	14
	Annex A (informative) Typical reference blocks	16
	Bibliography	18