

ISO 4652:2020 (E)

Rubber compounding ingredients — Carbon black — Determination of specific surface area by nitrogen adsorption methods — Single-point procedures

Contents

	Foreword
	Introduction
1	Scope
2	Normative references
3	Terms and definitions
4	Method A: Automatic gas chromatography (carrier gas method)
4.1	Principle
4.2	Apparatus
4.3	Reagents
4.4	Preparation of the sample portion
4.5	Degassing of sample
4.6	Measurement procedure
4.7	Validation
4.8	Expression of results
4.8.1	Results without correction
4.8.2	Results with correction
4.9	Correction by the multipoint nitrogen surface area (optional)
4.10	Test report
5	Method B: Automatic volumetric method
5.1	Principle
5.2	Apparatus
5.3	Reagents
5.4	Preparation of automatic volumetric adsorption measurement apparatus
5.5	Degassing of sample
5.5.1	General
5.5.2	Vacuum suction method
5.5.3	Purge gas flow method
5.6	Measurement procedure
5.7	Validation with SRB
5.8	Expression of results
5.9	Correction by the multipoint nitrogen surface area (optional)
5.10	Test report
6	Precision
Annex A	(informative) Correction by the multipoint nitrogen surface area
Annex B	(informative) Precision
B.1	General
B.2	Results
B.2.1	General
B.2.2	Repeatability
B.2.3	Reproducibility