ISO 23641:2021 (E)

Flexible cellular polymeric materials — Determination of antibacterial effectiveness

Contents

Foreword

Introduction

1 Scope

2 Normative references

3 Terms and definitions

4 Judgement criteria of antibacterial effectiveness

5 Test methods

5.1 Bacteria to be used for the tests
5.2 Reagents and materials
5.3 Equipment and apparatus
5.4 Sterilization methods
5.4.1 General
5.4.2 Dry-heat sterilization
5.4.3 High-pressure steam sterilization
5.4.4 Flame sterilization
5.5 Medium and buffer
5.5.1 General
5.5.2 1/500 nutrient broth medium (1/500 NB)
5.5.3 Slant culture medium
5.5.4 Standard nutrient agar medium (SA medium)
5.5.5 Phosphate-buffered physiological saline
5.6 Preservation of test strain
5.7 Procedure
5.7.1 General
5.7.2 Pre-culture of bacteria
5.7.3 Preparation of test specimens
5.7.4 Sterilization of specimens
5.7.5 Preparation of test inoculum
5.7.6 Inoculation onto the test specimens
5.7.7 Shaking incubation of the test specimens and the control group
5.7.8 Measurement of viable bacteria cell count
5.7.8.1 The just-after-inoculation control plot
5.7.8.2 The after-24-hours'-shaking control plot
5.7.8.3 The non-treated test plot
5.7.8.4 The antibacterial treated test plot
5.7.9 Notation of viable bacteria cell count
5.8 Expression of the results
5.8.1 Requirements for test validity
5.8.2 Calculation of the antibacterial activity value

6 Test report

Annex A (normative) Pour plate culture method

A.1 General
A.2 Test procedure

Page count: 13