

ISO 2782-1:2022-04 (E)

Rubber, vulcanized or thermoplastic - Determination of permeability to gases - Part 1: Differential-pressure methods

Contents		Page
Foreword		v
Introduction		vi
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	2
5	Pressure sensor method	2
5.1	Apparatus	2
5.2	Calibration	4
5.3	Test gas	4
5.4	Test pieces	5
5.4.1	Shape and dimensions	5
5.4.2	Preparation	5
5.4.3	Number of test pieces	5
5.4.4	Measurement of thickness	5
5.4.5	Time interval between forming and testing	5
5.5	Conditioning	5
5.6	Test conditions	5
5.7	Gas transmission area	6
5.8	Procedure	6
5.9	Calculation and expression of results	7
5.9.1	Gas transmission rate	7
5.9.2	Gas permeability coefficient	8
5.9.3	Gas diffusion coefficient	8
5.9.4	Gas solubility coefficient	8
6	Simplified pressure sensor method	9
6.1	Apparatus	9
6.1.1	Test cell	9
6.1.2	Test piece support	9
6.1.3	Two pressure sensors	9
6.1.4	Test gas supply reservoir	9
6.1.5	Temperature sensor	9
6.2	Calibration	10
6.3	Test gas	10
6.4	Test pieces	11
6.4.1	Shape and dimensions	11
6.4.2	Preparation	11
6.4.3	Number of test pieces	11
6.4.4	Measurement of thickness	11
6.4.5	Time interval between forming and testing	11
6.5	Conditioning	11
6.6	Test conditions	11
6.7	Gas transmission area	11
6.8	Procedure	11

6.9	Calculation and expression of results	12
6.9.1	Gas permeability coefficient	12
7	Gas-chromatographic method	12
7.1	Apparatus	12
7.2	Calibration	14
7.3	Test gas	14
7.4	Carrier gas	14
7.5	Test pieces	14
7.5.1	Shape and dimensions	14
7.5.2	Preparation	14
7.5.3	Number of test pieces	14
7.5.4	Measurement of thickness	14
7.5.5	Time interval between forming and testing	14
7.6	Conditioning	14
7.7	Test conditions	14
7.8	Gas transmission area	14
7.9	Calibration curve	14
7.10	Procedure	15
7.11	Calculation and expression of results	16
7.11.1	Gas transmission rate	16
7.11.2	Gas permeability coefficient	16
8	Test report	16
Annex A (normative)	Calibration schedule	18