

DIN EN ISO 21971:2024-12 (E)

Fine ceramics (advanced ceramics, advanced technical ceramics) - Mechanical properties of ceramic composites at ambient temperature in air atmospheric pressure - Determination of hoop tensile properties of tubes (ISO 21971:2019); English version EN ISO 21971:2024

Contents		Page
Foreword		v
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	3
5	Apparatus	4
5.1	Pressurizing system	4
5.2	Test specimen gripping and end closure	4
5.3	Strain measurement	5
5.3.1	General	5
5.3.2	Strain gauges	5
5.3.3	Digital image correlation	5
5.4	Pressure and data recording systems	6
5.5	Measurement of dimensions	6
6	Tubular test specimen	7
6.1	Specimen specifications	7
6.1.1	General	7
6.1.2	Dimension	7
6.1.3	Geometry	7
6.1.4	Tolerances and variability	8
6.2	Specimen preparation	8
6.2.1	General	8
6.2.2	As-fabricated	8
6.2.3	Application-matched machining	9
6.2.4	Customary practices	9
6.2.5	Standard procedure	9
6.3	Test count and test specimens sampling	9
7	Test procedure	9
7.1	General	9
7.2	Test mode and rates	9
7.3	Testing technique	10
7.3.1	Measurement of test specimen dimensions	10
7.3.2	Instrumentation of test specimen	10
7.3.3	Setting-up of strain measurement means	10
7.3.4	Measurements	11
7.3.5	Post-test analyses	12
7.4	Test validity	12
8	Calculation of results	12
8.1	Test specimen origin	12
8.2	Hoop tensile stress and strain	12
8.3	Hoop tensile strength and corresponding strain	13
8.4	Proportionality ratio or pseudo-elastic modulus in circumferential direction	14
8.4.1	Stress-strain curves with a linear region	14
8.4.2	Nonlinear stress-strain curves	14

8.5	Poisson's ratio (optional)	15
8.6	Statistics	15
9	Test report	15
9.1	General	15
9.2	Testing information	15
9.3	Test specimen and material	16
	9.3.1 Tubular test specimen drawing or reference	16
	9.3.2 Description of the test material	16
9.4	Equipment and test parameters	16
9.5	Test results	16
	Bibliography	18