

# ISO 3380:2002-12 (E)

## Leather - Physical and mechanical tests - Determination of shrinkage temperature up to 100 °C

---

<b>Contents</b>		<b>Page</b>
<b>Foreword</b> .....		<b>iv</b>
<b>1</b>	<b>Scope</b> .....	<b>1</b>
<b>2</b>	<b>Normative references</b> .....	<b>1</b>
<b>3</b>	<b>Principle</b> .....	<b>1</b>
<b>4</b>	<b>Apparatus</b> .....	<b>1</b>
<b>5</b>	<b>Sampling and sample preparation</b> .....	<b>3</b>
<b>6</b>	<b>Procedure</b> .....	<b>3</b>
<b>7</b>	<b>Test report</b> .....	<b>3</b>
<b>Annex A (informative) Sources of test apparatus</b> .....		<b>4</b>