

# ISO 12183:2005-02 (E)

## Nuclear fuel technology - Controlled-potential coulometric assay of plutonium

---

| <b>Contents</b>  |   | <b>Page</b> |
|--|---|-------------|
| Foreword .....   |   | iv          |
| <b>1</b>   | <b>Scope .....</b>  | <b>1</b>    |
| <b>2</b>   | <b>Normative references .....</b>                             | <b>1</b>    |
| <b>3</b>   | <b>Principle .....</b>  | <b>1</b>    |
| <b>4</b>   | <b>Reagents .....</b>   | <b>2</b>    |
| <b>5</b>   | <b>Apparatus .....</b>  | <b>2</b>    |
| <b>6</b>   | <b>Procedure .....</b>  | <b>7</b>    |
| <b>6.1</b>   | <b>Plutonium determination .....</b>                          | <b>7</b>    |
| <b>6.2</b>   | <b>Analysis of subsequent samples .....</b>                   | <b>12</b>   |
| <b>7</b>   | <b>Expression of results .....</b>                            | <b>12</b>   |
| <b>7.1</b>   | <b>Calculation of the electrical calibration factor .....</b> | <b>12</b>   |
| <b>7.2</b>   | <b>Calculation of the blank .....</b>                         | <b>12</b>   |
| <b>7.3</b>   | <b>Fraction of electrolysed plutonium .....</b>               | <b>13</b>   |
| <b>7.4</b>   | <b>Plutonium content .....</b>                                | <b>14</b>   |
| <b>7.5</b>   | <b>Quality control .....</b>                                  | <b>14</b>   |
| <b>8</b>   | <b>Characteristics of the method .....</b>                    | <b>14</b>   |
| <b>8.1</b>   | <b>Repeatability .....</b>                                    | <b>14</b>   |
| <b>8.2</b>   | <b>Confidence interval .....</b>                              | <b>14</b>   |
| <b>8.3</b>   | <b>Analysis time .....</b>                                    | <b>15</b>   |
| <b>9</b>   | <b>Interferences .....</b>                                    | <b>15</b>   |
| <b>10</b>  | <b>Procedure variations and optimisation .....</b>            | <b>17</b>   |
| <b>10.1</b>  | <b>Accountability measurements .....</b>                      | <b>17</b>   |
| <b>10.2</b>  | <b>Process control measurements .....</b>                     | <b>18</b>   |
| <b>10.3</b>  | <b>Measurement cell design .....</b>                          | <b>18</b>   |
| <b>10.4</b>  | <b>Electrolyte and electrode options .....</b>                | <b>18</b>   |
| <b>10.5</b>  | <b>Test sample size .....</b>                                 | <b>19</b>   |
| <b>10.6</b>  | <b>Background current corrections .....</b>                   | <b>19</b>   |
| <b>10.7</b>  | <b>Correction for iron .....</b>                              | <b>19</b>   |
| <b>10.8</b>  | <b>Control-potential adjustment .....</b>                     | <b>20</b>   |
| <b>Annex A (normative) Purification by anion-exchange separation .....</b>       |   | <b>21</b>   |
| <b>Annex B (normative) Determination of Formal Potential E<sub>0</sub> .....</b> |   | <b>23</b>   |
| <b>Bibliography .....</b>  |   | <b>24</b>   |