

DIN EN 843-2:2007-03 (E)

Advanced technical ceramics - Mechanical properties of monolithic ceramics at room temperature - Part 2: Determination of Young's modulus, shear modulus and Poisson's ratio

Contents		Page
Foreword		4
1	Scope	5
2	Normative references	5
3	Terms and definitions	6
4	Method A: Static flexure method	6
4.1	Principle	6
4.2	Apparatus	7
4.3	Test pieces	8
4.4	Procedure	8
4.5	Calculations	11
4.6	Measurement uncertainty	13
5	Method B: Resonance method	13
5.1	Principle	13
5.2	Apparatus	13
5.3	Test pieces	14
5.4	Procedure	16
5.5	Calculations	18
5.6	Measurement uncertainty	20
6	Method C: Ultrasonic method	20
6.1	Principle	20
6.2	Apparatus	20
6.3	Test pieces	22
6.4	Test method	22
6.5	Calculations	23
6.6	Measurement uncertainty	23
7	Method D: Impulse excitation method	24
7.1	Principle	24
7.2	Apparatus	24
7.3	Test pieces	24
7.4	Procedure	24
7.5	Calculations	27
7.6	Measurement uncertainty	27
8	Report	28
8.1	General	28
8.2	Method A	28
8.3	Method B	28
8.4	Method C	29
8.5	Method D	29
Annex A (informative)	Impact excitation method applied to disc test pieces	30

A.1	Scope	30
A.2	Apparatus	30
A.3	Test pieces	30
A.4	Principle	30
A.5	Method	31
A.6	Calculations	32
A.7	Interferences	32
A.8	Measurement uncertainty	33
A.9	Report	33
Annex B (informative) Round-robin validation of test methods		37
B.1	Objectives	37
B.2	Materials	37
B.3	Test facilities	37
B.4	Results	37
B.5	Conclusions	38
Bibliography		39