

DIN EN ISO 20427:2024-10 (E)

Pigments and extenders – Dispersion procedure for sedimentation-based particle sizing of suspended pigment or extender with liquid sedimentation methods (ISO 20427:2023)

Contents	Page
European foreword	3
Foreword	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Principles of dispersion	7
4.1 Principles of ultrasonic dispersion.....	7
4.2 Principle of wet jet mill dispersion.....	7
4.3 Principle of shaker-based dispersion.....	7
5 Principles of sedimentation-based techniques for particle size analysis	8
5.1 Stokesian sedimentation analysis.....	8
5.2 Disk-type centrifuges.....	8
5.3 Cuvette-type centrifuges.....	8
5.4 Gravitation-based sedimentation methods.....	8
5.5 Centrifugal field-flow fractionation method.....	9
6 Apparatus	9
7 Settings for dispersion	11
7.1 Procedure of ultrasonic dispersion using a probe-type sonicator.....	11
7.2 Procedure of ultrasonic dispersion using a bath-type sonicator.....	12
7.3 Procedure of shaker-based dispersion.....	12
8 Dispersion procedure	13
8.1 General.....	13
8.2 Sampling for dispersion.....	13
8.3 Reagents.....	13
8.4 Recommendations for sample preparation.....	14
9 Sampling	14
10 Measurement and expression of results	14
11 Test report	14
Annex A (normative) Protocol for the determination of energy input	16
Annex B (informative) Limits for ultrasonic dispersion procedure	19
Annex C (informative) Procedures for dispersion of TiO₂ pigments	20
Annex D (informative) Procedure for dispersion of CaCO₃ with wet jet milling	21
Annex E (informative) Procedure for the dispersion of Fe₂O₃ with an ultrasonic probe	22
Annex F (informative) Procedure for dispersion of carbon black	23
Annex G (informative) General procedure for dispersion of pigment or extender	24
Bibliography	26