

ISO 6529:2013-02 (E)

Protective clothing - Protection against chemicals - Determination of resistance of protective clothing materials to permeation by liquids and gases

Contents		Page
Foreword		iv
Introduction		v
1	Scope	1
2	Normative references	1
3	Terms and definitions	2
4	Principle	5
5	Choice of analytical technique and collection medium	5
5.1	General	5
5.2	Gaseous collection media	5
5.3	Liquid collection media	6
5.4	Other collection media	6
6	Apparatus	6
7	System configuration	8
7.1	Open-loop	8
7.2	Closed-loop	9
8	Detection	11
8.1	Frequency of analysis	11
8.2	Analytical methods	11
9	Sampling	12
9.1	Sampling procedure	12
9.2	Preparation of test specimens	13
9.3	Measurement of test specimen thickness and mass	13
10	Procedure	13
10.1	Pre-screening	13
10.2	Calibration	13
10.3	Validation	14
10.4	Preparation of test apparatus	14
10.5	Method A -- Liquid chemicals with continuous contact	15
10.6	Method B -- Gaseous chemicals with continuous contact	16
10.7	Method C -- Liquid or gaseous chemical with intermittent contact	18
10.8	Calculation of results	19
10.9	Visual assessment of test specimen	22
10.10	Repeat tests	22
11	Report	24
Annex A (informative)	Recommended list of chemicals for comparing permeation resistance of protective clothing materials	26
Annex B (informative)	Sources of permeation test cells and permeation test cell parts	29

Annex C (informative) Designs and specifications of commonly-used permeation test cells	31
Annex D (informative) Suggested procedures for calibrating and measuring the sensitivity of permeation-test systems	35
Annex E (informative) Testing the permeation resistance of seams and closures	39
Annex F (normative) Default conditions for testing and reporting permeation resistance	42
Annex G (informative) Inter-laboratory and inter-sample variation	43
Bibliography	45